

Zinc Phosphate PZ20

ZINC PHOSPHATE TETRAHYDRATE, $Zn_3(PO_4)_2 \cdot 4H_2O$

PZ20 0516G

ZINC PHOSPHATE



Description

Zinc Phosphate PZ20 is a corrosion inhibiting pigment suitable for a wide range of applications, from DIY to more demanding ones such as coil coating. It is a stable and non-hygroscopic white powder with a low tinting strength, it is easily dispersed.

Thanks to its low solubility, **Zinc Phosphate PZ20** is compatible with a wide range of solvent and water based resins.

Technical data

	Nominal Value	Tolerance (+/-)	
Zn content (%) - on the ignited product	50.0	2.0	ICP
PO ₄ content (%) - on the ignited product	48.0	2.0	ICP
Oil absorption (cm ³ /100 g)	27	5	ISO 787/5
Sieve residue - 45 µm (%)	0.05	max	ISO 787/7
pH	6.5	1.0	ISO 787/9
Pb Content (ppm)	100	max	ICP
Cd Content (ppm)	100	max	ICP
Density (g/ml)	Typ. 3.3		ISO 787/10
D50 (µm)	Typ. 4.5		Laser granulometry
Fineness	North	Typ. 7	ISO 787/5
	Hegman	Typ. 5.5	ISO 1524
Bonded water content (%) - 1h at 600°C	Typ. 15.7		Gravimetry
Recommended shelf life: 5 years			

Formulators Guidelines

Solvent Based

	Performance
Short oil alkyd	★★★
Medium/long oil alkyd	★★
High solid epoxy	★★
2K epoxy	★★
Epoxy ester	★★
PU	★★

Best performances are obtained with a typical loading of 5 to 12% by weight on the total formulation and a PVC ranging from 20% to 40%

Water Based

Water reducible resin	★★
Alkyd emulsion	★★
Epoxy ester	★★
2K epoxy	★★
Acrylics/modified acrylics	★★

Specialty coatings

Wash primer	★
Coil coating	★★★★*
Powder coating	

Excellent: ★★★ Good: ★★ Possible: ★ Not yet tested: ___
 Not recommended: nr * : Normally used in association with other pigments (ex: ion exchanged Silica)

SNCZ
L'ANTICORROSION

45/49, Chaussée Jules César - F-95250 BEAUCHAMP
 Technical Support : tech.support@sncz.net
 Tél : +33 1 30 40 57 57

www.sncz.com

Supersedes: PZ20 075G
 18/05/2016

TEDS/COMMERCIAL 998 V0.03

The information presented herein is true and accurate to the best of our knowledge, but without any guarantee unless explicitly given. Since the conditions of use are beyond our control we disclaim any liability, including for patent infringement, incurred in connection with the use of these products, data or suggestion.